

### **LISTING OF THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application.

1(currently amended): High burring, high strength, hot-rolled steel sheet excellent in softening resistance of the weld heat affected zone characterized by consisting essentially of,

by wt%,

C: 0.01 to 0.1%,

Si: 0.01 to 2%,

Mn: 0.05 to 3%,

P≤0.1%,

S≤0.03%,

Al: 0.005 to 1%,

N: 0.0005 to 0.005%, ~~and~~

Ti: 0.05 to 0.5%, and

Nb: 0.01 to 0.5%

and further containing C, S, N, Ti, Nb, Cr, and Mo in ranges satisfying

~~0%<C-(12/48Ti-12/14N-12/32S)≤0.05% and~~

0% < C-(12/48Ti +12/93Nb - 12/14N-12/32S)≤0.05%, and

Mo+Cr≥0.2%, Cr≤0.5%, and Mo≤0.5%,

the balance comprising Fe and unavoidable impurities, wherein the microstructure is composed of only bainitic ferrite and bainite,

wherein an effective amount of solid solution C is present in said hot-rolled welded steel sheet to form carbon clusters or precipitates with Mo and Cr to achieve excellent softening resistance at the weld heat affected zone when welded.

Claim 2: (canceled).

3 (currently amended): High burring, high strength, hot-rolled steel sheet excellent in softening resistance of the weld heat affected zone as set forth in claim 1 ~~or 2~~, characterized by further consisting essentially of, by wt%, one or two of Ca: 0.0005 to 0.002%, a REM: 0.0005 to 0.02%, and B: 0.0002 to 0.002%.

4 (currently amended): High burring, high strength, hot-rolled steel sheet excellent in softening resistance of the weld heat affected zone as set forth in claim 1 ~~or 2~~, characterized by being automotive thin steel sheet coated with zinc.

Claims 5 to 9: (canceled).

10 (currently amended): High burring, high strength, hot-rolled steel sheet excellent in softening resistance of the weld heat affected zone as set forth in claim 1 ~~or 2~~ characterized by consisting essentially of,

by wt%,

C: 0.01 to 0.1%,

Si: 0.01 to 2%,

Mn: 0.05 to 3%,

P≤0.1%,

$S \leq 0.03\%$ ,

Al: 0.005 to 1%,

N: 0.0005 to 0.005%, and

Ti: 0.05 to 0.5%

and further containing C, S, N, Ti, Cr, and Mo in ranges satisfying

$0\% < C - (12/48Ti - 12/14N - 12/32S) \leq 0.05\%$  and

$Mo + Cr \geq 0.2\%$ ,  $Cr \leq 0.5\%$ , and  $Mo \leq 0.5\%$ ,

the balance comprising Fe and unavoidable impurities, wherein the microstructure is composed of only bainitic ferrite and bainite, ~~and~~ wherein the bainitic ferrite ~~and bainite structures~~ structure contained in the hot-rolled steel sheet before welding does not ~~including~~ include carbides inside ferrite laths and between ferrite laths other than Ti and Nb carbides.